


SEW830 GT Filter media


FR blended cellulose 15/85




Whitw
Weis



0,3
DENIER



0,56
mm



F8/F9
EN779-2002



130
gram



MD 550N/5cm Length
CD 400N/5cm cross

FILTER MEDIA DATA

SEW830 is a FR blended cellulose filter media with synthetic fibers (15% Polyester) no-curing and latex impregnation with flame retardant coating
SEW830 has high hydrophobic properties, with high tensile strength for long pulse jet cleaning cycles



Dry
Trocken

80 Celsius

Wet
Feuchte

- Celsius

Air Permeability | 200Pa
Luftdurchlässigkeit | 200Pa

630 m3/m2/hr

Chemical Resistance | Chemische Eigenschaften

	Excellent Sehr Gur	Good Gut	Fair Mässig
Oil/water resistance Öl und Wasserabweisend	X	X	X
Hydrolysis resistance Hydrolysebeständigkeit	X	X	
Acid resistance Säurebeständigkeit	X	X	X
Alkaline resistance Alkalienbeständigkeit	X		



Phone +45 5460 2080



Test Report
No.
15-0756F

S.E.W. North Filtration A/S * Vesterbrogade1, Section C * DK-4930 Maribo
E-mail: sales@northfiltration.com * www.northfiltration.com * VAT no.: DK 33 49 28 71