

SEW830 GT Filter media

FR blended cellulose 15/85



Whitw Weis	0,3 DENIER	0,56 mm	F8/F9 EN779-2002	130 gram	MD 550N/5cm Length CD 400N/5cm cross

FILTER MEDIA DATA

SEW830 is a FR blended cellulose filter media with synthetic fibers (15% Polyester) no-curing and latex impregnation with flame retardant coating
SEW830 has high hydrophobic properties, with high tensile strength for long pulse jet cleaning cycles



Dry Trocken **80 Celsius**

Wet Feuchte **- Celsius**

Air Permeability | 200Pa Luftdurchlässigkeit | 200Pa **630 m3/m2/hr**

Chemical Resistance | Chemische Eigenschaften

	Excellent Sehr Gut	Good Gut	Fair Mässig
Oil/water resistance Öl und Wasserabweisend	X	X	X
Hydrolysis resistance Hydrolysebeständigkeit	X	X	
Acid resistance Säurebeständigkeit	X	X	X
Alkaline resistance Alkalienbeständigkeit	X		



Test Report No. 15-0756F

Phone +45 5460 2080

S.E.W. North Filtration A/S * Vesterbrogade1, Section C * DK-4930 Maribo
E-mail: sales@northfiltration.com * www.northfiltration.com * VAT no.: DK 33 49 28 71