

SEW153 PTFe Antistatic


100% Polyester PTFe + aluminiums coated




Grey
Grau



2,0/2,2
Decitex



0,56
mm



0,09
%



268
gram



MD 512,4 N/5cm Length
CD 518,3N/5cm cross

FILTER MEDIA DATA

SEW 153 is a 100% PTFe and aluminium coated spun bond filter media that is manufactured from continuous fibre which does not permit the particles to become embedded.

SEW 153 is very rugged and has a high burst strength, and is used in very static and abrasive loaded environments. 100% Spun bond media makes pulse cleaning easier and is running with lower pressure drop. SEW 153 is a washable filter media. (limited)



Dry
Trocken

120 Celsius

Wet
Feuchte

90 Celsius

Air Permeability | 200Pa
Luftdurchlässigkeit | 200Pa

500 m³/m²/hr

Chemical Resistance | Chemische Eigenschaften

	Excellent Sehr Gut	Good Gut	Fair Mässig
Oil/water resistance Öl und Wasserabweisend	X	X	X
Hydrolysis resistance Hydrolysebeständigkeit	X	X	X
Acid resistance Säurebeständigkeit	X	X	X
Alkaline resistance Alkalienbeständigkeit	X	X	X



Certificate No.

Phone +45 5460 2080

S.E.W. North Filtration A/S * Vesterbrogade 1, Section C * DK-4930 Maribo
E-mail: sales@northfiltration.com * www.northfiltration.com * VAT no.: DK 33 49 28 71